

Average Weight: 4.42g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die					0.328204	7.425%
	Silicon (Si)	7440-21-3	100.00	Basis	0.328204	
Solder Bump					0.015849	0.359%
	Tin (Sn)	7440-31-5	98.20	Basis	0.015564	
	Silver (Ag)	7440-22-4	1.80	Basis	0.000285	
Solder Paste					0.008320	0.188%
	Tin (Sn)	7440-31-5	96.50	metal	0.008029	
	Silver (Ag)	7440-22-4	3.00	metal	0.000250	
	Copper (Cu)	7440-50-8	0.50	metal	0.000042	
Capacitor 1					0.019200	0.434%
	Barium oxide	1304-28-5	30.22	Ceramic	0.005802	
	Titanium dioxide	13463-67-7	15.11	Ceramic	0.002901	
	Misc.	trade secret	5.04	Ceramic	0.000968	
	Nickel (Ni)	7440-02-0	33.44	Inner electrode	0.006420	
	Copper (Cu)	7440-50-8	11.87	Outer electrode	0.002279	
	Silicon dioxide	7631-86-9	1.06	Outer electrode	0.000204	
	Boric oxide	1303-86-2	0.26	Outer electrode	0.000050	
	Nickel (Ni)	7440-02-0	0.81	Nickel Plating Layer	0.000156	
	Tin (Sn)	7440-31-5	2.19	Tin Plating Layer	0.000420	
Capacitor 2					0.017670	0.400%
	Barium oxide	1304-28-5	31.67	Ceramic	0.005596	
	Titanium dioxide	13463-67-7	15.83	Ceramic	0.002797	
	Misc.	trade secret	5.28	Ceramic	0.000933	
	Nickel (Ni)	7440-02-0	26.67	Inner electrode	0.004713	
	Copper (Cu)	7440-50-8	15.10	Outer electrode	0.002668	
	Silicon dioxide	7631-86-9	1.34	Outer electrode	0.000237	
	Boric oxide	1303-86-2	0.33	Outer electrode	0.000058	
	Nickel (Ni)	7440-02-0	1.00	Nickel Plating Layer	0.000177	
	Tin (Sn)	7440-31-5	2.78	Tin Plating Layer	0.000491	

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Underfill					0.044000	0.995%
	Bisphenol F type liquid epoxy resin	9003-36-5	15.00	Basis	0.006600	
	1,6-Bis(2,3-epoxypropoxy)naphthalene	27610-48-6	10.00	Basis	0.004400	
	Bisphenol A type liquid epoxy resin	25068-38-6	5.00	Basis	0.002200	
	Amine type hardener	trade secret	10.00	Basis	0.004400	
	Silicon dioxide	60676-86-0	58.00	Filler	0.025520	
	Carbon black	1333-86-4	1.00	Color agent	0.000440	
	Additives	trade secret	1.00	Additives	0.000440	
Solder Ball					0.751829	17.010%
	Tin (Sn)	7440-31-5	96.50	Main Material	0.725515	
	Silver (Ag)	7440-22-4	3.00	Main Material	0.022555	
	Copper (Cu)	7440-50-8	0.50	Main Material	0.003759	
Substrate					3.234928	73.188%
	Copper (Cu)	7440-50-8	34.41		1.113139	
	Tin (Sn)	7440-31-5	0.81		0.026203	
	Lead (Pb)	7439-92-1	0.00		0.000000	
	Silver (Ag)	7440-22-4	0.03		0.000970	
	BT Core	N/A	51.59		1.668899	
	ABF	N/A	11.48		0.371370	
	Solder Mask	N/A	1.68		0.054347	

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
04/03/2015	1.0	Initial Xilinx release

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.