



100% Material Declaration Data Sheet for UltraScale FFVA1517

PK694 (v1.0) December 15, 2014

Average Weight: 14.944g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die					0.474641	3.176%
	Silicon (Si)	7440-21-3	100.00	Basis	0.474641	
Solder Bump					0.022556	0.151%
	Tin (Sn)	7440-31-5	98.20	Basis	0.022150	
	Silver (Ag)	7440-22-4	1.80	Basis	0.000406	
Solder Paste					0.011968	0.080%
	Tin (Sn)	7440-31-5	96.50	Metal	0.011549	
	Silver (Ag)	7440-22-4	3.00	Metal	0.000359	
	Copper (Cu)	7440-50-8	0.50	Metal	0.000060	
Capacitor 1					0.035200	0.236%
	Barium oxide	1304-28-5	30.22	Ceramic	0.010637	
	Titanium dioxide	13463-67-7	15.11	Ceramic	0.005319	
	Misc.	trade secret	5.04	Ceramic	0.001774	
	Nickel (Ni)	7440-02-0	33.44	Inner electrode	0.011771	
	Copper (Cu)	7440-50-8	11.87	Outer electrode	0.004178	
	Silicon dioxide	7631-86-9	1.06	Outer electrode	0.000373	
	Boric oxide	1303-86-2	0.26	Outer electrode	0.000092	
	Nickel (Ni)	7440-02-0	0.81	Nickel Plating Layer	0.000285	
	Tin (Sn)	7440-31-5	2.19	Tin Plating Layer	0.000771	
Capacitor 2					0.022000	0.147%
	Barium oxide	1304-28-5	31.67	Ceramic	0.006967	
	Titanium dioxide	13463-67-7	15.83	Ceramic	0.003483	
	Misc.	trade secret	5.28	Ceramic	0.001162	
	Nickel (Ni)	7440-02-0	26.67	Inner electrode	0.005867	
	Copper (Cu)	7440-50-8	15.10	Outer electrode	0.003322	
	Silicon dioxide	7631-86-9	1.34	Outer electrode	0.000295	
	Boric oxide	1303-86-2	0.33	Outer electrode	0.000073	
	Nickel (Ni)	7440-02-0	1.00	Nickel Plating Layer	0.000220	
	Tin (Sn)	7440-31-5	2.78	Tin Plating Layer	0.000612	

© Copyright 2014 Xilinx, Inc. XILINX, the Xilinx logo, Virtex, Spartan, ISE, and other designated brands included herein are trademarks of Xilinx in the United States and other countries. All other trademarks are the property of their respective owners

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Underfill					0.062000	0.415%
	Bisphenol F type liquid epoxy resin	9003-36-5	15.00	Basis	0.009300	
	1,6-Bis(2,3-epoxypropoxy)naphthalene	27610-48-6	10.00	Basis	0.006200	
	Bisphenol A type liquid epoxy resin	25068-38-6	5.00	Basis	0.003100	
	Amine type hardener	trade secret	10.00	Basis	0.006200	
	Silicon dioxide	60676-86-0	58.00	Filler	0.035960	
	Carbon black	1333-86-4	1.00	Color agent	0.000620	
	Additives	trade secret	1.00	Additives	0.000620	
Lid					6.840000	45.771%
	Copper (Cu)	7440-50-8	98.35	Main Material	6.727140	
	Nickel (Ni)	7440-02-0	1.65	Main Material	0.112860	
Lid Adhesive					0.180000	1.204%
	Aluminium Oxide Al ₂ O ₃	1344-28-1	80.00	Main Material	0.144000	
	Dimethyl siloxane, dimethylvinyl-terminated	68083-19-2	20.00	Main Material	0.036000	
Solder Ball					1.267250	8.480%
	Tin (Sn)	7440-31-5	96.50	Main Material	1.222896	
	Silver (Ag)	7440-22-4	3.00	Main Material	0.038018	
	Copper (Cu)	7440-50-8	0.50	Main Material	0.006336	
Substrate					6.028385	40.340%
	Copper (Cu)	7440-50-8	40.49		2.440602	
	Tin (Sn)	7440-31-5	0.64		0.038371	
	Lead (Pb)	7439-92-1	0.00		0.000006	
	Silver (Ag)	7440-22-4	0.02		0.001193	
	BT Core	N/A	43.11		2.598947	
	ABF	N/A	14.24		0.858362	
	Solder Mask	N/A	1.51		0.090906	

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
12/15/2014	1.0	Initial Xilinx release

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.