



PK958 (v1.0) June 12, 2018

100% Material Declaration Data Sheet for UltraScale + FLGA 2577

Average Weight : 45.6607 g

Component	Substance Description	CAS # or Description	% of component	Use in product	Component weight / substance weight (in grams)	Component % of total
Silicon die	Silicon	7440-21-3	100.00	basis	1.210854	2.65%
					1.210854	
Micro-bump	Copper	7440-50-8	54.80	metal	0.052306	0.21%
	Nickel	7440-02-0	22.69	metal	0.021653	
	Tin	7440-31-5	21.87	metal	0.020876	
	Silver	7440-22-4	0.64	metal	0.000613	
					0.581180	
Micro-bump underfill	Amorphous silica	trade secret	46.87	filler	0.272388	1.27%
	Amine compound	trade secret	20.84	glue	0.121095	
	Epoxy resin compound-A	trade secret	15.627	glue	0.090821	
	Epoxy resin compound-B	trade secret	15.627	glue	0.090821	
	Epoxy resin compound-C	trade secret	1.042	glue	0.006055	
					0.130315	
Mold compound	Silica filler	trade secret	86.022	filler	0.112099	0.29%
	Epoxy resin	trade secret	8.602	glue	0.011210	
	Hardener resin	trade secret	5.376	glue	0.007006	
Interposer die	Silicon	7440-21-3	100.000	basis	0.273600	0.60%
C4 Bump	Copper	7440-50-8	5.407	metal	0.008154	0.33%
	Nickel	7440-02-0	3.223	metal	0.004861	
	Tin	7440-31-5	57.532	metal	0.086763	
	Lead	7439-92-1	33.838	metal	0.051031	
					0.053198	
Solder Paste	Tin	7440-31-5	96.5	metal	0.051336	0.42%
	Silver	7440-22-4	3	metal	0.001596	
	Copper	7440-50-8	0.5	metal	0.000266	
C4 Underfill	Bisphenol F/ epichlorohydrin copolymer	9003-36-5	24	basis	0.045750	0.42%
	Phenolic resin	trade secret	19	basis	0.036219	
	Bisphenol A type liquid	25068-38-6	4	basis	0.007625	
	Amine type accelerator	trade secret	5	basis	0.009531	
	Silicon dioxide	60676-86-0	44.1	basis	0.084065	
	Carbon black	1333-86-4	0.9	basis	0.001716	
	Additives	trade secret	3	additive	0.005719	
Lid	Copper	7440-50-8	99.64	main material	26.006247	57.16%
	Nickel	7440-02-0	0.36	main material	0.093961	
				main material	0.148522	
Lid Adhesive	Silicone	Confidential	80	main material	0.118818	0.33%
	Others	Confidential	20	main material	0.029704	
Lid TIM	Aluminum oxide	1344-28-1	85	main material	0.609861	1.57%
	Zinc oxide	1314-13-2	5	main material	0.035874	
	Silicone	Confidential	9	main material	0.064574	
	Others	Confidential	1	main material	0.007175	
				main material	1.906632	
Solder Ball	Tin	7440-31-5	96.5	main material	1.839900	4.18%
	Silver	7440-22-4	3	main material	0.057199	
	Copper	7440-50-8	0.5	main material	0.009533	
Capacitor 1	Titanium Dioxide	13463-67-7	15.11		0.009718	0.14%
	Misc		5.04		0.003241	
	Nickel	7440-02-0	33.44	inner electrode	0.021506	
	Copper	7440-50-8	11.87	out electrode	0.007634	
	Silicon Dioxide	7631-86-9	1.06		0.000682	
	Diboron trioxide; Boric	1303-86-2	0.26		0.000167	
	Nickel	7440-02-0	0.81	plating1	0.000521	
	Tin	7440-31-5	2.19	plating2	0.001408	
	Other		30.22		0.019435	
					0.024223	
	Capacitor 2	BaTiO3 type	12047-27-7	51.1	ceramic	
Copper		7440-50-8	27	inner electrode	0.006540	
Nickel		7440-02-0	16.9	out electrode	0.004094	
Nickel		7440-02-0	2	plating1	0.000484	
Tin		7440-31-5	3	plating2	0.000727	
Substrate	Copper	7440-50-8	37.06		5.193324	30.69%
	Tin	7440-31-5	0.34		0.047645	
	Lead	7439-92-1	0.11		0.015415	
	Core	N/A	47.21		6.615673	
	ABF	N/A	14.16		1.984281	
	Solder Mask	N/A	1.11		0.155547	
					14.013287	

Revision History

Date	Version	Description of Revisions
6/12/2018	1.0	Initial Xilinx release.

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.